



Printed On: Feb 10, 2014

INSPECTION INFORMATION

Specific Gravity @ 60°F (15.6°C)
Viscosity @ 40°C cSt
Viscosity @ 100°C cSt
Pour Point °C (°F)
Viscosity Index
Color
Gravity, °API
Brookfield Viscosity at -40°C, cP

TEST METHOD

ASTM D4052
ASTM D445
ASTM D445
ASTM D5950
ASTM D2270
ASTM D 1500
ASTM D287
ASTM D2983

TYPICAL VALUE

0.8611
37.86
7.45
-51°C (-60°F)
168
Red
32.82
18,500

CLAIMS INFORMATION

Dexron III, Dexron II, Dexron
Mercon, Ford ESP-M2C166-H
GM 9985010
Ford M2C195-A1
Chrysler MS-5931

Meets Requirements
Meets Requirements
Suitable for Use
Suitable for Use
Suitable for Use